

**MIG/MAG WELDING
WIRES**

TECHNICAL SPECIFICATION SHEET

Co2 Mig Welding Wire

Sizes (mm) :

0.60, 0.80, 0.90, 1.00, 1.20, 1.40, 1.60

Grades :

AWS - 5.18 ER 70S 6,

IS - 6419 S-4

EN – 440 G 46 3 M G4 Si 1

Packing :

100% Precision Layer Winded in Plastic Spools

5 kg / 12.5 kg / 15 kg

Fibre Drum Pack. :- 100 kgs / 250 kgs



Applications :

Automobile Body, Chassis, Frames and Brackets

Automobile Silencers, Petrol/Diesel/Gas Tanks & all other Automobile, Scooter, Cycle spare parts & accessories, LPG Gas Cylinders, Compressors, Railway Wagons, Boilers, Poles & Steel Towers. Steel furniture, Scaffoldings, Gratings & all other welding in steel fabrication

WELDING CURRENT SETTINGS AND PARAMETERS

S.No	SIZE in MM	CURRENT (DC+) AMPS	CURRENT (DC+) VOLTS	GAS FLOW L/M
1	Ø 0.60	50 -- 150	18 -- 25	10 -- 25
2	Ø 0.80	50 -- 180	18 -- 25	10 -- 25
3	Ø 0.90	80 -- 200	18 -- 25	10 -- 25
4	Ø1.00	80 -- 200	20 -- 26	12 -- 20
5	Ø1.20	130 -- 300	22 -- 36	15 -- 25
6	Ø1.60	200 -- 400	24 -- 38	16 -- 28

CHEMICAL COMPOSITION OF WELD METAL

C %	Mn %	Si %	S %	P %	Cr %	Ni %	V %	Mo %	Cu %
0.06--0.15	1.40--1.85	0.80--1.15	0.035	0.025	0.15	0.15	0.03	0.15	0.5

Note :- Single values mentioned above are maximum*

MECHANICAL PROPERTIES OF WELD METAL

U.T.S (N/mm ²)	Y .S. (N/mm ²)	ELONGATION (L = 4d)%	IMPACT (CVN) AT -30°C
490	400	22	27 J

Note :- Single values mentioned above are Minimum.

*FOR APPROVALS AND CERTIFICATIONS KINDLY CONTACT :- info@rasielectrodes.com

storage - Store in warm and dry place.

*All statements, information and data given are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.

www.rasielectrodes.com

RASI ELECTRODES LIMITED,

REDHILLS, CHENNAI - 52 | info@rasielectrodes.com | www.rasielectrodes.com | customer care no. - 044-26401822